

## Vistamaxx™ 6202

### Performance Polymer

#### Product Description

Vistamaxx 6202 is primarily composed of isotactic propylene repeat units with random ethylene distribution, and is produced using ExxonMobil's proprietary metallocene catalyst technology. It has excellent elastomeric properties, is easy to process and is compatible with a wide variety of materials. It is particularly good for thermoplastic compounding which requires excellent filler dispersion and acceptance.

#### Key Features

- Suitable for a wide range of film and compounding applications which require high filler acceptance such as sound deadening sheets and masterbatches.
- Other typical applications include calendered or extruded sheet/profiles and injection molded goods.
- Excellent adhesion to conventional or metallocene PP and PE.
- Very good elasticity and toughness.
- Very low seal initiation temperature combined with high seal strength when used as sealing layer of co-extruded structures.
- Very good chemical resistance and long term aging.
- Particularly good for thermoplastic and polyolefinic blends where a balance of flexibility, transparency and impact performance is required.
- RoHS compliant.

#### General

Availability <sup>1</sup>	<ul style="list-style-type: none"> <li>• Africa &amp; Middle East</li> <li>• Asia Pacific</li> </ul>	<ul style="list-style-type: none"> <li>• Europe</li> <li>• Latin America</li> </ul>	<ul style="list-style-type: none"> <li>• North America</li> </ul>
Applications	<ul style="list-style-type: none"> <li>• Calendered Profiles</li> <li>• Calendered Sheeting</li> <li>• Cast Film</li> </ul>	<ul style="list-style-type: none"> <li>• Extruded Profiles</li> <li>• Extruded Sheeting</li> <li>• Injection Molding</li> </ul>	<ul style="list-style-type: none"> <li>• PP/TPE Modification</li> </ul>
Uses	<ul style="list-style-type: none"> <li>• Compounding</li> </ul>	<ul style="list-style-type: none"> <li>• Film</li> </ul>	<ul style="list-style-type: none"> <li>• Packaging</li> </ul>
RoHS Compliance	<ul style="list-style-type: none"> <li>• RoHS Compliant</li> </ul>		
Form(s)	<ul style="list-style-type: none"> <li>• Pellets</li> </ul>		
Revision Date	<ul style="list-style-type: none"> <li>• 01/01/2017</li> </ul>		

Physical	Typical Value (English)	Typical Value (SI)	Test Based On
Density <sup>2</sup>	0.862 g/cm <sup>3</sup>	0.862 g/cm <sup>3</sup>	ASTM D1505
Melt Index <sup>2</sup> (190°C/2.16 kg)	9.1 g/10 min	9.1 g/10 min	ASTM D1238
Melt Mass-Flow Rate (MFR) <sup>2</sup> (230°C/2.16 kg)	20 g/10 min	20 g/10 min	ExxonMobil Method
Ethylene Content	15 wt%	15 wt%	ExxonMobil Method

Hardness	Typical Value (English)	Typical Value (SI)	Test Based On
Durometer Hardness (Shore A)	64	64	ASTM D2240

Mechanical	Typical Value (English)	Typical Value (SI)	Test Based On
Tensile Stress at 100%	318 psi	2.19 MPa	ASTM D638
Tensile Stress at 300%	374 psi	2.58 MPa	ASTM D638
Tensile Strength at Break	> 800 psi	> 5.52 MPa	ASTM D638
Tensile Set	15 %	15 %	ExxonMobil Method
Elongation at Break	> 800 %	> 800 %	ASTM D638
Flexural Modulus - 1% Secant	1860 psi	12.8 MPa	ASTM D790

Elastomers	Typical Value (English)	Typical Value (SI)	Test Based On
Tear Strength (Die C)	183 lbf/in	32.0 kN/m	ASTM D624

Thermal	Typical Value (English)	Typical Value (SI)	Test Based On
Vicat Softening Temperature	113 °F	45.2 °C	ExxonMobil Method

## Vistamaxx™ 6202 Performance Polymer

### Additional Information

Please contact Customer Service for food law compliance information.

For data specific to chemical resistance, refer to the Technical Literature (TL), Chemical Resistance of Vistamaxx Performance Polymer.

### Legal Statement

This product, including the product name, shall not be used or tested in any medical application without the prior written acknowledgement of ExxonMobil Chemical as to the intended use. For detailed Product Stewardship information, please contact Customer Service.

### Processing Statement

Vistamaxx polymers have a wide temperature processing window. A good starting point for temperatures is 10°C above the highest melting point. This material does not require drying and can be compounded or used in a dry blend. Use conventional processing knowledge to ensure mixing of the materials.

### Notes

Typical properties: these are not to be construed as specifications.

<sup>1</sup> Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.

<sup>2</sup> Property specified in conventional unit of measure.

For additional technical, sales and order assistance: [www.exxonmobilchemical.com/ContactUs](http://www.exxonmobilchemical.com/ContactUs)

©2019 ExxonMobil. ExxonMobil, the ExxonMobil logo, the interlocking "X" device and other product or service names used herein are trademarks of ExxonMobil, unless indicated otherwise. This document may not be distributed, displayed, copied or altered without ExxonMobil's prior written authorization. To the extent ExxonMobil authorizes distributing, displaying and/or copying of this document, the user may do so only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. You may not copy this document to or reproduce it in whole or in part on a website. ExxonMobil does not guarantee the typical (or other) values. Any data included herein is based upon analysis of representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, suitability, accuracy, reliability, or completeness of this information or the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. This document is not an endorsement of any non-ExxonMobil product or process, and we expressly disclaim any contrary implication. The terms "we," "our," "ExxonMobil Chemical" and "ExxonMobil" are each used for convenience, and may include any one or more of ExxonMobil Chemical Company, Exxon Mobil Corporation, or any affiliate either directly or indirectly stewarded.

[exxonmobilchemical.com](http://exxonmobilchemical.com)