

Honam EVA VA800
Ethylene Vinyl Acetate Copolymer
Honam Petrochemical Corporation



Prospector

General			
Material Status	• Commercial: Active		
Availability	• Asia Pacific		
Features	• Good Adhesion	• Good Processability	
Uses	• Adhesives	• Automotive Applications	• Coating Applications

Physical	Nominal Value Unit	Test Method
Density	0.950 g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	20 g/10 min	ASTM D1238
Vinyl Acetate Content	28.0 wt%	
Hardness	Nominal Value Unit	Test Method
Rockwell Hardness	25	ASTM D785
Thermal	Nominal Value Unit	Test Method
Vicat Softening Temperature	< 40.0 °C	ASTM D1525
Melting Temperature	69.0 °C	

Notes

¹ Typical properties: these are not to be construed as specifications.

