

# LOTTE CHEMICAL

**SEETEC VA900**

Ethylene Vinyl Acetate Copolymer

## General Information

### Description

SEETEC VA900 resin is produced by ExxonMobil Chemical's autoclave process technology. SEETEC VA900 resin, with 28% VA content, is an excellent raw material in the application of hot melt adhesives.

### Additives

- ◆ Antioxidant
- ◆ Free flow agent

### Applications

- ◆ Hot melt adhesives

## Physical Properties<sup>1</sup>

Properties	Nominal Value	Unit	Test Method
Melt Index	150.0	g/10min	ASTM D1238
Vinyl Acetate	28	wt. %	LC Method
Density	0.950	g/cm <sup>3</sup>	ASTM D1505
Melting Point	67	°C	LC Method
Hardness	21	D scale	ASTM D2240
Vicat Softening Point	< 40	°C	ASTM D1525

### NOTE

ISO 9001, 14001, /TS 16949

<sup>1</sup> Physical Properties : these are not to be construed as specifications
