



Arak Petrochemical Company



ISO 9001:2000  
Certificate No.: CH98/8032

ISO 14001:2004  
Certificate No.: CH03/0112

OHSAS 18001:1999  
Certificate No.: CH05/0675

**Address:**

No. 3, Taban St.  
Vali-e-Asr Ave.  
Tehran - IRAN

**Tel:**

(+98 21)82122700

**Fax:**

(+98 21)8867 4126-27

**Web-site:**

www.arpc.ir

**E-mail:**

Sales@arpc-ir.net

## Polypropylene

### Moplen Z30S (Fibre)

Typical properties	Test method (ASTM)	Unit	Value
MFR @230°C, 2.16 kg	D1238/L	gr/10min	25
Flexural Modulus	D790	Mpa	1500
Notched Izod Impact@23°C	D256	J/m	30
Tensile Strength@Yield	D638	Mpa	32
Elongation@Yield	D638	%	13
Vicat Softening Point, 10N	D1525	°C	152
HDT(0.46N/mm <sup>2</sup> )	D648	°C	94
Rockwell Hardness	D785	R.Scale	100
Oven Aging@150°C	D3012	Hours	150

➤ Values shown are averages & are not to be considered as product specifications.

#### ❖ Main application & Characteristics:

Moplen Z30S is a high melt flow homo-polymer polypropylene for the production of CF, BCF and staple fibres at medium to high spinning speeds.

Moplen Z30S offers a high homogeneity, stable extrusion and excellent process ability on both short and long spinning lines. This grade allows a high stretch ratio and gives tough and resilient fibres.

Moplen Z30S is suitable for low denier staple fibres for non-woven fabrics, diapers, medical-sanitary applications and wipes.

Another typical application is high tenacity continuous filament for straps for backpacks, handles for big and safety belts.

Continuous filament with medium tenacity is used for upholstery, sportswear and heavy duty clothing.

Moplen Z30S is also suited for the production of bulked continuous filament for thermo bonding and carpets.

\* Moplen Z30S is suitable for food contact.