



台橡股份有限公司  
TSRC CORPORATION  
A MEMBER OF CEC GROUP

Head office : 18F, No.95,Dun Hua South Road,, Sec. 2, Taipei, Taiwan 105, R.O.C.

Tel : 886-2-3701 6000 Fax : 886-2-3701 6868

Kaohsiung Plant : 2 Hsing Kung Road, Ta-She, Kaohsiung, Taiwan 815, R.O.C.

Tel : 886-7-351 3811-9

Fax : 886-7-351 8050

Jan 2008

# TAIPOL SBS 3206



Polymerization System	Solution Polymerization, styrene-butadiene block copolymer
Stabilizer	Non-staining
Characteristics	Low molecular weight, high strength, easy processing, and good solubility in common adhesive solvent
Use	Plastics modification, adhesive and other goods

<u>Polymer Properties</u>	<u>Specification Range</u>		<u>Test Method</u>
	<u>min</u>	<u>max</u>	
Bound styrene (%)	27.5	30.5	K62-TPPC-09
Volatile matter (%)	—	0.5	K62-TPFP-01
Yellow index	—	10.0	K62-TPFP-04
Ash (%)	—	0.2	ASTM D-5667
Specific gravity	0.95 Typical		ASTM D-792
Gel (%)	—	0.1	K62-TPFP-16
Melt flow(190? /5kg) (g/10min.)	2.0	8.0	ASTM D-1238
Hardness (Type A)	75 Typical		ASTM D-2240