

Globalprene 3501 Styrene-Butadiene block copolymer 苯乙烯-丁二烯嵌段共聚物

Features 特性:		Typical Application 一般應用:			
• Linear block copolymer	線型嵌段共聚物	• Plastics modification	塑料改質		
• High strength and low viscosity	高強度及低黏度	• Asphalt modification	瀝青改質		
• High tensile strength	高引張強度	• Compounding for modification	混煉改質		
• High rebound	高回復性	• Mechanical parts	機械零件		
Typical Properties		Test Method	Unit	Typical Value	Range
一般性質		測試方法	單位	數值	範圍
SM Content 苯乙烯含量		ASTM D5775	%	31	30.5~33.5
Specific Gravity 比重		ASTM D792		0.94	N/A
Volatile Matter 揮發份		ASTM D5668	%	0.25	≤0.5
Ash Content 灰份		ASTM D5667	%	0.3	≤1.0
25wt% Toluene Viscosity 25wt% 甲苯黏度		ASTM D2196	CP	5350	4500~6000

Packing 包裝 : 12kg paper bag 12 公斤紙袋
400kg super bag 400 公斤太空袋
800lb super bag 800 磅太空袋

All ingredients in the product are in compliance with the following chemical inventories:
United States: Toxics Substances Control Act Inventory (TSCA)
Europe: European Inventory of Existing Chemical Substances (EINECS)
Canada: Canadian Domestic/ Non-Domestic Substances List (DSL)
Philippines: Philippines Inventory of Chemicals and Chemical Substances (PICCS)
Australia: Australian Inventory of Chemical Substances
Korea: Korean Existing Chemicals List (KECL)
China: Inventory of Existing Chemical Substances Manufactured or Imported in China (IECSC)
 EU Directive 2002/95/EC RoHS (Restriction of certain Hazardous Substances)
 EC No 1907/2006 SVHC (Substances of Very High Concern)
 CEN Standard EN71.3
 Organo-tin Compounds

Product Stewardship Information 產品責任資訊

The values quoted here are typical of the grade, however, it is important to recognize that some variation around these values is to be expected as a result of uncertainties associated with measurement of the specific property and due to the normal variations encountered during the manufacturing process.
 以上所列之各項數據為實驗參考值，唯因使用時加工條件及環境之不同，而產生之差異非本公司所能保證與控制。

Head office 總公司	台北市八德路四段 83 號 3 樓 3F, No.83, Sec. 4, Bade Road, Taipei 105, Taiwan	Tel : 886-2-2763-1611 Fax : 886-2-27645749
USA office 美國	4803 Decker Drive Baytown, Texas 77520, USA	Tel : 1-281-424-6100 Fax : 1-281-424-6169
China office 中國	廣東省惠州市大亞灣經濟技術發展區石化大道中 299 號 299 Shihua Dadaozhong, Dayawan Economic and Technological Development Zone, Huizhou, Guangdong, China 516082	Tel : 86-752-5599000 Fax : 86-752-5599002

