

## SIBELITE® M3000 - M4000 - M6000

**SIBELITE®** is a high-purity silica produced from cristobalite by iron-free grinding and accurate sieving by means of air-separators.  
A controlled particle size distribution, the excellent optical properties, chemical inertness and constant whiteness lead to benefits in paints, plastics etc...

### GRANULOMETRIC DATA AND PHYSICAL CHARACTERISTICS

	M3000	M4000	M6000		Method
control-sieve > 40 µm	≤ 1	≤ 0.04	≤ 0.02	%	Alpine
D10	4.5	3	1.5	µm	Malvern MS 2000
D50	17	6	4	µm	Malvern MS 2000
D90	40	12	8	µm	Malvern MS 2000
<i>D50</i>	<i>14</i>	<i>5</i>	<i>3</i>	<i>µm</i>	<i>Malvern MS X</i>
density	2.3	2.3	2.3	kg/dm <sup>3</sup>	
bulk density	0.7	0.46	0.42	kg/dm <sup>3</sup>	
specific surface	1.5	3.5	5	m <sup>2</sup> /g	BET
	5600	10000	16500	cm <sup>2</sup> /g	Blaine
oil absorption	26	27	28	g/100 g	
hardness	6.5	6.5	6.5	Mohs	
pH	9	9	9		
colour	L* 98	98	98		Minolta CM-3610d
	a* 0.03	0.02	0.01		D65/10°
	b* 0.57	0.33	0.27		
coeff. of thermal expansion range: 20-300°C	54	54	54	x 10 <sup>-6</sup> K <sup>-1</sup>	
refractive index	1.48	1.48	1.48		

TDS.03.05.31 2010-03-19 1/2

Sibelco Benelux  
De Zate 1 - BE-2480 Dessel  
tel. +32 14 83 72 11 - fax +32 14 83 72 12  
www.sibelco.be

Technical Data

## SIBELITE® M3000 - M4000 - M6000

# Technical Data

### CHEMICAL ANALYSIS (XRF) %

	M3000	M4000	M6000
SiO <sub>2</sub>	99.5	99.5	99.5
Fe <sub>2</sub> O <sub>3</sub>	0.03	0.03	0.03
Al <sub>2</sub> O <sub>3</sub>	0.20	0.20	0.20
TiO <sub>2</sub>	0.02	0.02	0.02
K <sub>2</sub> O	0.05	0.05	0.05
CaO	0.01	0.01	0.01



The above given information is based on mean values. The typical properties and chemical analyses are intended as examples and are not to be considered as substitutes for actual testing and analyses in those situations where properties and chemical compositions are critical factors. Sales and supplies will always be according to our general sales conditions.

CAS-Nr.: 14464-46-1

EINECS-Nr.: 238-455-4

MSDS available on request

ed.09

TDS.03.05.31 2010-03-19 2/2

Sibelco Benelux  
De Zate 1 - BE-2480 Dessel  
tel. +32 14 83 72 11 - fax +32 14 83 72 12  
www.sibelco.be

