

WHT-6420

Description	WHT-6420 is polyester-based TPU hot-melt adhesive, supplied in form of white or slightly yellowish pellets with the characteristic of high viscosity, fast crystallization rate, and good adhesion strength to PVC, PU, fabric and genuine leather.
Application	Solution adhesive for footwear, fabric coatings, hot-melt adhesive film and tape.
Working instructions	WHT-6420 is generally used as solutions in MEK, EAc, TOL, THF, or Acetone, with 15~20% solid content. While WHT-6420 is used as hot-melt, the characteristics of the extruder are the followings: <ul style="list-style-type: none"> • L/D ratio between 25:1 and 30:1 for extrusion. • The extruder screw must have 3 zones and a compression ratio between 2:1 and 3:1. Screws with a compression ratio greater than 4:1 should be avoided. • The extruder screw should have a continuous regulation device and a working power higher than for processing other plastics.

For optimum results, previous drying of the product during 3-6 hours at 40~50°C is advisable, in a hot air circulatory, vacuum or desiccant-air dryer. The suggested processing-temperature profiles for injection are depicted in the table below.

T-die Extrusion Guideline for WHT-6420

Product	Die (°C)	Metering (°C)	Compression(°C)	Feed (°C)	Drying temperature(°C)	Drying time (h)
6420	180	175	165	150	30-45	3-6

Note: The actual processing temperature should be adjusted properly while auxiliary materials were used.

Regind usage

Where end-use requirements permit, up to 20% resin regind may be used with virgin material, provided that the material is kept free of contamination and is properly dried (see section on Drying). Any regind used must be generated from properly molded/extruded parts, sprues, runners, trimmings, and/or films. All regind used must be clean, uncontaminated, and thoroughly blended with virgin resin prior to drying and processing. Under no circumstances should degraded, discolored, or contaminated material be used for regind. Materials of this type should be discarded. Improperly mixed and/or dried regind may diminish the desired properties. It is critical that you test finished parts produced with any amount of regind to ensure that your end-use performance requirements are fully met.

Disclaimer

The information provided here is for reference only. The specification will be provided in the quality certificate or in the contract. It is the user's responsibility to test the material and its suitability for a process. We have no control over what another party does with the material and we cannot take any responsibility for another party's action. Nor will we be responsible for any indirect damages while using our products. The user is welcome to contact our customer and technical service center with questions on our products

Property

PROPERTY	Method	Units	6420
Density	ASTM D 792	g/cm ³	1.2
Tensile strength	ASTM D 412	MPa	44
Ultimate elongation	ASTM D 412	%	700
Solution viscosity (15% in MEK, 23°C)	ISO 3219	mPa.s	1500~2200
Crystallization Rate			Very Fast
Suggested Activation temperature		°C	60~100

These products can only be ordered in typical quantities. Please contact your sales representative for details.