

## Sipchem EVA 2518 CO

18% Ethylene Vinyl Acetate copolymer

**Product description:** Sipchem EVA 2518 CO is an 18% ethylene vinyl acetate copolymer resin, designed for a variety of foam moulding application; manufactured by IPC an affiliate of Sipchem in The Kingdom of Saudi Arabia using an Exxon-Mobil high-pressure tubular process. EVA 2518 CO exhibits low melting temperature, excellent processability and mechanical properties.

**Applications:** Foams, Shoe Soles, Injection Moulding, Profile Extrusion and Compounds

**Additives:** Thermal Stabiliser: 300 ppm      Antiblock: No      Slip: No

Properties	Typical Value	Unit	Test Method
Melt Index (190°C / 2.16 kg)	2.5	g/10 min	ASTM D1238
Vinyl Acetate Content	18	wt%	ASTM D5594
Density	0.935	g/cm <sup>3</sup>	ASTM D1505
Vicat Softening Point	64	°C	ASTM D1525
Melting Point	87	°C	ASTM D3418
Tensile Strength at Yield	5.2	MPa	ASTM D638
Tensile Strength at Break	11	MPa	ASTM D638
Elongation at Yield	260	%	ASTM D638
Elongation at Break	>800	%	ASTM D638
Flexural Modulus	60	MPa	ASTM D790
Hardness Shore A	76		ASTM D2240
Hardness Shore D	36		ASTM D2240

1. These are typical properties: these are not to be construed as specifications.
2. This product is not intended for use in medical applications and should not be used in any such applications.
3. Contact your Sipchem Representative for potential food contact application compliance.

### Compliance & Product Stewardship Department

#### Contact Details:

Website: [www.sipchem.com](http://www.sipchem.com)  
Email: [marketing@sipchem.com](mailto:marketing@sipchem.com)  
Phone: +966 13 359 3372

#### Disclaimer

Before using the product listed above, customers and other users should take care in determining the suitability of such product for the intended use. SIPCHEM do not accept any liability whatsoever arising from the use of this information or the use, application or processing of any product described herein.