

SABIC® EVA 2518DF

EHTYLENE-VINYL ACETATE



DESCRIPTION

SABIC EVA 2518DF is designed for foaming applications with low temperature resistance and excellent process ability and elastic behavior. It contains 18% ethylene vinyl acetate copolymer resin with good loading properties with many fillers. SABIC EVA 2518DF contains thermal stabilizer. It does not contain any anti-block nor slip agent. The product is manufactured via autoclave process.

TYPICAL APPLICATIONS

- o Foam (footwear, sports, and leisure), thermal insulation, and sealants
- o Toys

TYPICAL PROPERTY VALUES

Revision 20220704

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
POLYMER PROPERTIES			
Melt Flow Rate (MFR)			
@ 2.16kg	2.5	g/10 min	ISO 1133
VA Content			
Vinyl content	18	wt%	ISO 8985
MECHANICAL PROPERTIES ⁽¹⁾			
Tensile Strength at Break ⁽²⁾	20	MPa	ASTM D638
Tensile Elongation at Break ⁽²⁾	800	%	ASTM D638
Durometer Hardness			
Durometer Hardness (D)	38	D	ASTM D2240
THERMAL PROPERTIES			
Vicat Softening Temperature			
Vicat Softening Temperature*1 @10N	59	°C	ASTM D1525
Melting Temperature			
Melting Point	86	°C	SABIC method

(1) Test specimen preparation method: compression

(2) Test Speed 500 mm/min

PROCESSING CONDITIONS

Typical processing temperature: 150 - 180 °C.

STORAGE AND HANDLING

SABIC EVA 2518DF should be stored in a dry and cool place with an adequate ventilation and Storage and shall be protected from UV-light at a temperature below 50 °C. It is advisable to process polyethylene resins within 6 months after the delivery.



DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

