

Grade	Structure	Block ratio	300% stretching strength	Ensil strength MPA	Elongation %	Permanent SET %	Hardness shore A	Toluene Solution Viscosity at 25°C and 25% mpa.s
YH-502/502T	Linear	30/70	4.0	27.0	540	16	73	180

Grade	Structure	Block ratio	300% stretching strength	Ensil strength MPA	Elongation %	Permanent SET %	Hardness shore A	Toluene Solution Viscosity at 25°C and 25% mpa.s
YH-501/501T	Linear	30/70	5.0	20.0	490	24	76	600
YH-502/502T	Linear	30/70	4.0	27.0	540	16	73	180
YH-503/503T	Linear	33/67	6.0	25.0	480	16	74	2300
YH-504/504T	Linear	31/69	5.0	26.0	480	12	74	
YH-561/561T	Mixed	33/67	6.5	26.5	490	20	80	1200
YH-602/602T	Star-shaped	35/65	6.5	27.0	500	36	81	250
YH-688	Star-shaped	13/87	1.4	10.0	800	4	45	
YH-604/604T	Star-shaped	33/67	5.8	30.0	530	20	78	2200